

Appl. No. 10/534,607
Reply to Office Action of December 13, 2005

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (Currently Amended): A silver halide photographic material comprising on one side of a paper support having resin coat layers on both sides of a base paper one or more light-sensitive layers and one or more light-insensitive layers, wherein after the photographic material of an L-size (having a length of 89 mm in a machine direction of the base paper and a length of 127 mm vertical to the machine direction) is processed, the photographic material exhibits an image clarity (C-value) of 20% to 60% which is determined using a 1.0 mm optical wedge in accordance with JIS K 7105; and the photographic material comprising a light-insensitive hydrophilic colloid layer between a light-sensitive layer closest to the support and the support, the light-insensitive hydrophilic colloid layer containing a mercapto-heterocyclic compound.

Appl. No. 10/534,607
Reply to Office Action of December 13, 2005

Claim 2 (Canceled) .

Claim 3 (Original): The silver halide photographic material as claimed in claim 1, wherein the light-insensitive hydrophilic colloid layer contains a thiosulfonic acid compound.

Claim 4 (Original): The silver halide photographic material as claimed in claim 1, wherein the light-insensitive hydrophilic colloid layer contains a latex.

Claim 5 (Original): The silver halide photographic material as claimed in claim 1, wherein the light-insensitive hydrophilic colloid layer contains a lipophilic compound dispersion.

Claim 6 (Original): The silver halide photographic material as claimed in claim 1, wherein the light-insensitive hydrophilic colloid layer contains a titanium oxide.

Claim 7 (Original): The silver halide photographic material as claimed in claim 1, wherein the light-insensitive hydrophilic colloid layer contains a colloidal silver.

Appl. No. 10/534,607
Reply to Office Action of December 13, 2005

Claim 8 (Previously Presented): The silver halide photographic material as claimed in claim 1, wherein the light-sensitive layer closest to the support is a blue-sensitive layer containing silver halide grains having an average grain size of 0.35 to 0.60 μm .

Claim 9 (Canceled).

Claim 10 (Previously Presented): The silver halide photographic material as claimed in claim 3, wherein the light-sensitive layer closest to the support is a blue-sensitive layer containing silver halide grains having an average grain size of 0.35 to 0.60 μm .

Claim 11 (Previously Presented): The silver halide photographic material as claimed in claim 4, wherein the light-sensitive layer closest to the support is a blue-sensitive layer containing silver halide grains having an average grain size of 0.35 to 0.60 μm .

Claim 12 (Previously Presented): The silver halide photographic material as claimed in claim 5, wherein the light-sensitive layer

Appl. No. 10/534,607
Reply to Office Action of December 13, 2005

closest to the support is a blue-sensitive layer containing silver halide grains having an average grain size of 0.35 to 0.60 μm .

Claim 13 (Previously Presented): The silver halide photographic material as claimed in claim 6, wherein the light-sensitive layer closest to the support is a blue-sensitive layer containing silver halide grains having an average grain size of 0.35 to 0.60 μm .

Claim 14 (Previously Presented): The silver halide photographic material as claimed in claim 7, wherein the light-sensitive layer closest to the support is a blue-sensitive layer containing silver halide grains having an average grain size of 0.35 to 0.60 μm .

Claim 15 (New): A silver halide photographic material comprising on one side of a paper support having resin coat layers on both sides of a base paper one or more light-sensitive layers and one or more light-insensitive layers, wherein after the photographic material of an L-size (having a length of 89 mm in a machine

Appl. No: 10/534,607
Reply to Office Action of December 13, 2005

direction of the base paper and a length of 127 mm vertical to the machine direction) is processed, the photographic material exhibits an image clarity (C-value) of 20% to 60% which is determined using a 1.0 mm optical wedge in accordance with JIS K 7105; and the photographic material comprising a light-insensitive hydrophilic colloid layer between a light-sensitive layer closest to the support and the support and the light-insensitive hydrophilic colloid layer containing a mercapto-heterocyclic compound and wherein the light-sensitive layer closest to the support is a blue-sensitive layer contains silver halide grains having an average grain size of 0.35 to 0.60 μm .